

**Standards**

TS EN ISO 2560-A	: E 46 6 B 42 H5
EN ISO 2560-A	: E 46 6 B 42 H5
AWS A5.1	: E 7018 - 1 H4

**Chemical Composition of  
Weld Metal % (Typical)**

C	Si	Mn
0.08	0.4	1.4

**Mechanical Properties\***

Yield Strength (N/mm <sup>2</sup> )	Tensile Strength (N/mm <sup>2</sup> )	Impact Strength (ISO-V/-60°C)	Elongation (L <sub>0</sub> =5d <sub>0</sub> ) (%)
min. 460	530-650	min. 47 J	min. 24

\* CTOD tested

**Typical Base Material Grades**

- S235JR-E295, E335, S235J2G3-S355J2G3, P235T1-P355T1, P235T2,P355T2, L210NB-L415NB, L290MB-L360MB, P235G1TH, P255G1TH, P235GH-P355GH, S235JRS1-S235J4S, S315G1S-S355G3S, S255N-S380N, P255NH-P355NH, S255NL-S460NL1, GE200-GE300
- API 5L: X42, X46, X52, X56, X60, X65

**Features and Applications**

- Suitability for use in welding of high-strength, fine-grained steels
- High ductility at low temperatures down to -60°C
- It is used for joining thick materials safely
- Weld metal recovery of approx. 120%
- Requirement of re-drying for minimum 2 hours at the temperatures between 300°C and 350°C
- CTOD tested.

**Welding Positions**

**Current Type**

D.C.(+)

**Operating Data**

Product Code	Diameter x Length (mm) / (inch)		Welding Current (A)	Weight g / 100 pcs
3010100423	2.50 x 350	3/32 x 14"	80 - 100	2380
3010100426	3.20 x 350	1/8 x 14"	100 - 140	3740
3010100432	4.00 x 450	5/32 x 18"	130 - 190	7000

**Approvals:** TSE, BV, ABS, CE, GOST-R, SEPRO