

**FLUX F-SH1** TS EN 1045: FH 10

This flux is flour based and used with application of silver alloyed brazing materials. Working temperature is between 550 and 750°C. This flux is used on all base metals except aluminium and aluminium alloys. This product is sold as both powder and paste form

**FLUX F-LH1**

This is a flour based flux used for welding and brazing applications of aluminium and aluminium alloyed materials. Working temperature is between 500°C and 650°C and sold in powder form

**Operating Data**

<b>Product</b>	<b>Product Code</b>	<b>Application Materials</b>	<b>Package Weight (Kg)</b>
FLUX F-SH1 (powder)	6031100020	Silver	1
FLUX F-LH1 (powder)	6031100018	Aluminium	2