

Submerged ARC Welding Flux Shocking and Conditioning Ovens

- By using standalone thermostats in 2 separate compartments, welding flux is kept at high temperatures for shocking process and relatively kept in lower temperatures for drying and for resting process until they are taken to the application site.
- After its first use, submerged welding flux is kept at a temperature range of 300°C min. - 350° max. for two hours before being subjected to shock.
- In the second phase, the temperature in the oven is lowered to 130°C and the flux is kept in the oven until it is transferred to the application area.

GKTSD - 250kg + 250kg Double Digital Shocking and Conditioning Oven with Thermostat



General Data

Capacity	50+50kg / 100kg
Height (y)	120cm
External Diameter (g)	110x65cm
Max Heating Temperature	0 - 400°C
Heat Control	With Double Digital Control
Operating Capacity	3000+3000W / 6000W
Operating Voltage	380-400V
Operating Current	28A
Heat Insulation	Available
Weight	150kg

Standard and Optional Equipment

6051700016 This Order Code Relates to All Equipment

GKTSD - 350kg + 350kg Double Digital Shocking and Conditioning Oven with Thermostat



General Data

Capacity	350+350kg / 700kg
Height (y)	170cm
External Diameter (g)	220x90cm
Max Heating Temperature	0 - 400°C
Heat Control	With Double Digital Control
Operating Capacity	4500+4500W / 9000W
Operating Voltage	380-400V
Operating Current	41A
Heat Insulation	Available
Weight	390kg

Standard and Optional Equipment

6051700017 This Order Code Relates to All Equipment