

Standards

TS EN ISO 2560-A	: E 38 0 RC 11
EN ISO 2560-A	: E 38 0 RC 11
AWS A5.1	: E 6013

**Chemical Composition of
Weld Metal % (Typical)**

C	Si	Mn
0.06	0.3	0.5

Mechanical Properties

Yield Strength (N/mm ²)	Tensile Strength (N/mm ²)	Impact Strength (ISO-V/0°C)	Elongation (L ₀ =5d ₀) (%)
min.390	470-590	min.47 J	min.22

Typical Base Material Grades

- S 235JR, S275JR, S235J2G3-S355J2G3, P235 GH, P265 GH, P255NH, P235T1-P355T1, P235T2-P355T2, P235G1TH, P255G1TH, L210-L360NB, S235JRS1-S235J2S1, S235JRS2-S235J2S2

Features and Applications

- Electrode coating of flexible type, providing electrode bendability
- Suitability for welding at vertical-down position
- Deep penetration

Welding Positions

Current Type

D.C.(-) / A.C.

Operating Data

Product Code	Diameter x Length (mm) / (inch)		Welding Current (A)	Weight g / 100 pcs
3010100129	2.50 x 350	3/32 x 14"	60 - 110	1850
3010100132	3.20 x 350	1/8 x 14"	90 - 140	2940
3010100138	4.00 x 350	5/32 x 14"	110 - 180	4250
3010100141	4.00 x 450	5/32 x 18"	110 - 200	5460

Approvals: TSE, CE, SEPRO