

**Standards**

TS EN ISO 2560-A	: E 42 4 B 42 H5
EN ISO 2560-A	: E 42 4 B 42 H5
AWS A5.1	: E 7018 H4

**Chemical Composition of  
Weld Metal % (Typical)**

C	Si	Mn
0.07	0.5	1.0

**Mechanical Properties**

Yield Strength (N/mm <sup>2</sup> )	Tensile Strength (N/mm <sup>2</sup> )	Impact Strength (ISO-V/-40°C)	Elongation (L <sub>0</sub> =5d <sub>0</sub> ) (%)
min. 420	510-600	min. 47 J	min. 24

**Typical Base Material Grades**

- S235JR-E295, E335, S235J2G3-S355J2G3, C22, C35, P235T1-P355T1, P235T2,P355T2, L210-L360, L290MB-L360MB, P235G1TH, P255G1TH, P235GH-P295GH, S235JRS1-S235J4S, S315G1S-S355G3S, S255N-S355N, P255NH-P355NH, S255NL-S355NL, GE200-GE300
- API 5L: A, B, X42, X46, X52, X56, X60

**Features and Applications**

- Suitability for use in out-of-position welding except for welding at vertical down position
- Excellent strength and toughness
- Suitability for use in the fields of steel constructions, boiler, container, machine manufacturing and shipbuilding as well as for use in welding low-purity and high-carbon steels
- Suitability for the formation of welding buffer layers when building up high-carbon steels
- Weld deposits with very low hydrogen content
- Weld metal recovery of about 120%
- Requirement of re-drying for minimum 2 hours at the temperatures between 300°C and 350°C

**Welding Positions**

**Current Type**

D.C. (+)

**Operating Data**

Product Code	Diameter x Length (mm) / (inch)		Welding Current (A)	Weight g / 100 pcs
3010100351	2.50 x 350	3/32 x 14"	80 - 110	2410
3010100354	3.20 x 350	1/8 x 14"	100 - 140	3790
3010100363	4.00 x 450	5/32 x 18"	130 - 190	6850
3010100369	5.00 x 450	3/16 x 18"	190 - 240	10715

**Approvals:** BV, DNV-GL, TL, DB, ABS, LR, RS, RINA, NK, TSE, TÜV, CE, SEPRO, RCB, CWB, HAKC, CE