

Standards

TS EN ISO 21952-A	: G Z CrMo 1 Si
EN ISO 21952-A	: G Z CrMo 1 Si
TS EN ISO 21952-A	: W Z CrMo1 Si
EN ISO 21952-A	: W Z CrMo1 Si
AWS A5.28	: ER 80 S-B2

Chemical Composition of Welding Wire % (Typical)

C	Si	Mn	Mo	Cr
0.10	0.6	0.5	0.5	1.2

Mechanical Properties

Yield Strength (N/mm ²)	Tensile Strength (N/mm ²)	Impact Strength (ISO-V/+20°C)	Elongation ((L ₀ =5d ₀) (%))	Heat Treatment
min. 470	550 - 670	min. 47 J	min. 19	620°C/1hour-300°C air

Typical Base Material Grades

- 13CrMo4-5, 15CrMo5, 42CrMo4, 16CrMoV4, 25CrMo4, 24CrMo5, G22CrMo5-4, G17CrMo5-5, A 333Gr, P11

Features and Applications

- Used for the welding of high heat resisting. Cr-Mo alloyed steels which are used for the production of boilers tubes and pipes and nitrided steels
- Weld metal is resistant to temperatures up to +570°C
- Shielding gases: MAG; Ar+CO₂ and Ar+ O₂ mix gases, TIG; pure Ar gas can be used

Welding Positions



Current Type

TIG D.C.(-) / MAG D.C.(+)

Operating Data

Product Code		Diameter x Length (mm) / (inch)		Weight (Kg)	Package Type
BS 300	D 300				BS/D/300
3010201750	3010201776	0.8	0.030"	15	D 200
3010201752	3010201778	1.0	0.040"	15	D 100
3010201754	3010201780	1.2	0.047"	15	ECO PACK
3010201755	3010201782	1.6	0.062"	15	BIG PACK
		(0,6,0,9, 1,14,1,4)		(1,5,15,18,50,250,400)	
3010300326		1,60 x 1000	1/16 x 39"	5	Carton Box
3010300327		2,00 x 1000	5/64 x 39"	5	
3010300328		2,40 x 1000	3/32 x 39"	5	
3010300329		3,20 x 1000	1/8 x 39"	5	
3010300330		4,00 x 1000	5/32 x 39"	5	

Approvals: CE, SEPRO