

Standards

TS EN ISO 2560-A	: E 42 O RC 11
EN ISO 2560-A	: E 42 O RC 11
AWS A5.1	: E 6012

**Chemical Composition of
Weld Metal % (Typical)**

C	Si	Mn
0.06	0.35	0.45

Mechanical Properties

Yield Strength (N/mm ²)	Tensile Strength (N/mm ²)	Impact Strength (ISO-V/0°C)	Elongation (L ₀ =5d ₀) (%)
min. 420	510-610	min.47 J	min.22

Typical Base Material Grades

- S 235JR, S275JR, S235J2G3-S355J2G3, P235 GH, P265 GH, P255NH, P235T1 - P355T1, P235T2-P355T2, P235G1TH, P255G1TH, L210-L360NB, S235JRS1-S235J2S1, S235JRS2-S235J2S2

Features and Applications

- Electrode coating with medium-thickness
- Electrode coating of flexible type, providing electrode bendability
- Usability in welding of materials at hardly-reachable places
- Suitability for welding at vertical down position

Welding Positions

Current Type

D.C.(-) / A.C.

Operating Data

Product Code	Diameter x Length (mm) / (inch)		Welding Current (A)	Weight g / 100 pcs
3010100120	2.50 x 350	3/32 x 14"	60 - 110	1730
3010100123	3.20 x 350	1/8 x 14"	90 - 140	2900
3010100126	4.00 x 350	5/32 x 14"	130 - 180	4275

Approvals: TSE, CE, SEPRO